



## TECHNICAL DATA SHEET

<b>Materialorigin:</b>	<b>PVC – WINDOW</b>
<b>Materialspecification: Product</b>	<b>GRANULAT white (Pellets)</b> 0.11.00.100.000.00.00.00.150
Test results	
<b>Color:</b> CIE LAB system	L > 90,5 a no specification b <3,9
<b><u>THERMAL STABILITY:</u></b> DIN 53 381, proceed B, Nitrogen	≈ 78 min
<b><u>VICAT SOFTENING POINT:</u></b> DIN ISO 306, proceed B/50	≈ 82 °C
<b><u>MODULUS OF ELASTICITY:</u></b> DIN EN ISO 527 – 1	≈ 2400 N/mm <sup>2</sup>
<b><u>FLEXURAL IMPACT TEST (a<sub>k</sub>):</u></b> DIN ISO 179/1eA	≈ 20,5 kJ/m <sup>2</sup>
<b><u>K-VALUE</u></b> determination of Viskosity DIN 53726	64
<b><u>APPARENT DENSITY:</u></b> DIN 53466	0,85 g/cm <sup>3</sup>
<b><u>IMPURITIES:</u></b>	<0,02%